
CLASSIFICATION OF REACTION TO FIRE ACCORDANCE WITH EN 13501-1:2018

1. Introduction

This classification report defines the classification assigned to Induline LW-716 WF [iac] colorless in accordance with the procedures in EN 13501-1:2018.

Sponsor: Remmers GmbH
Bernhard-Remmers-Straße 13
49624 Lönigen, Germany

Prepared by: SYCHTA LABORATORIUM Sp. J.
Laboratorium Badań Palności Materiałów
ul. Ofiar Stutthofu 90
72-010 Police, Poland

Notified Body No: -

Product name: Induline LW-716 WF [iac] colorless

Classification report No: SL/Z-082/EN13501/0060a/2023

Date of issue: 09.02.2023

This classification report consists of four pages and may only be used or reproduced in its entirety.

2. Details of classified product

2.1. General

The product, Induline LW-716 WF [iac] colorless

2.2. Product description

The product, Induline LW-716 WF [iac] colorless, is described below or is described in the reports provided in support of classification listed in 3.1

348200 Induline LW-716 WF [iac] colorless
 Coating: 2x 80-120 mL/m²
 Carrier material: flame resistant MDF board (B-s1, d0, 19mm thick)

3. Reports and results in support of this classification

3.1. Specific conditions

-

3.2. Reports

Name of Laboratory	Name of sponsor	Report ref. No.	Test method and date Field of application rules and date
Sychta Laboratorium	Remmers GmbH	SL/Z-082/EN13823/0059a/2023	PN-EN ISO 13823 PN-EN ISO 11925-2 06.02 and 08.02.2023

3.3. Results

Test method and test number	Parameter	No. Tests ^a	Results	
			Continuous parameter - mean (m)	Compliance with parameters
PN-EN 13823	FIGRA, W·s ⁻¹	3	177	(-)
	THR _{600s} , MJ		6,4	(-)
	LFS < edge		(-)	Compliant
	SMOGRA, m ² ·s ⁻²		1	(-)
	TSP600s, m ²		32	(-)
	Flaming particles or droplets, time s		(-)	Compliant
PN-EN ISO 11925-2 Exposure time 30 s	Flame spread > 150 mm in 60 s, mm	6	(-)	Compliant
	Ignition of paper		(-)	Compliant

^a Not for extended application, (-): not applicable

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1:2018.

4.2. Classification

The product, Induline LW-716 WF [iac] colorless, in relations to its reaction to fire behaviour is classified:

C

The additional classification in relations to smoke production is:

s1

The additional classification in relations to flaming droplets / particles is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation products is:

Fire behaviour		Smoke production			Flaming droplets	
C	-	s	1	,	d	0

Reaction to fire classification: C-s1,d0

4.3. Field of application

This classification is valid for the following product parameters:

- wall panels approx. 19,0 mm thick
- weight per unit area 14,4 kg/m²
- density about 760 kg/m³


The classification is valid for the following end use applications:

This classification applies to material applied on MDF panels flame-retardant Euroclass B, according to DIN EN 13501 B-s1, d0 CE according to EN 13966 E1.

5. Limitations

This classification document does not represent type approval or certification of the product.

*Signature of person
undertaking classification:*



dr inż. Krzysztof Sychta

*Signature of person
authorising report:*



SYCHTA LABORATORIUM Sp. J.
72-010 Police, ul. Ofiar Stutthofu 90
tel./fax +48 91 4210 214, tel. 502078855
e-mail: biuro@sychta.eu www:sychta.eu
KRS 0000387681 REGON 321023120
NIP 8513152392

KIEROWNIK TECHNICZNY

dr inż. Krzysztof Sychta